

MACRO

LAMINATED FRONTLIT

CARACTERISTICI	DATA	METODA de TESTARE
Greutate	450gsm	ISO3801:1977
Tesatura	1000x1000 denier 18x18 fd / inch	DIN60001/DIN EN ISO2060
Tipul coatingului	PVC	N/A
Rezistenta la tractiune	2450N/5cm (L)	ISO527/3:1995
	2117N/5cm (W)	
Rezistenta la rupere	275N/5cm (L)	ISO4674/1:2003
	216N/5cm (W)	
Rezistenta la lipire	60N/5cm	DIN53357:1982
Rezistenta la temperaturi scazute	-22°F / -30°C	ISO13934-1:1999
RF Weldable (Heat Sealable)	YES	DIN53354

APLICATII:	Banere, Unipol, Billboar, Sisteme de expnere
COMPATIBILITARE CERNEALA:	UV, Latex, Solvent, Eco-Solvent, Screen Printing



CERTIFIED FOR HP LATEX INKS